

# TECHNICAL DATA SHEET

## POLYETHYLENE TIPELIN BS 501-17

### HDPE for blow moulding

TIPELIN / TIPOLEN / TIPPLEN / TATREN / BRALEN

The joint product portfolio of TVK and SLOVNAFT provides infinite opportunities

#### DESCRIPTION

**TIPELIN BS 501-17** is a high density polyethylene copolymer (with hexen-1 as comonomer) grade for blow moulding of products which require excellent ESCR and chemical resistance, furthermore balanced mechanical properties. The grade contains antioxidants.

#### APPLICATIONS

**TIPELIN BS 501-17** is recommended for bottles and cans up to 10 litre capacity for aggressive household chemicals and detergents. It is suitable for corrugated pipes too.

**TIPELIN BS 501-17** is suitable for food contact, for manufacturing of pharmaceutical packing products and toys. The product complies with Food Contact, Pharmaceutical and Toy Safety Regulations.

#### PROPERTIES

|   | Test method   | Unit              | Typical value |
|---|---------------|-------------------|---------------|
| Melt Mass-Flow Rate (MFR) (190 °C /2.16 kg) | ISO 1133-1    | g/10 min          | 0.18          |
| Melt Mass-Flow Rate (MFR) (190 °C /5.0 kg)  | ISO 1133-1    | g/10 min          | 0.94          |
| Melt Mass-Flow Rate (MFR) (190 °C /21.6 kg) | ISO 1133-1    | g/10 min          | 22            |
| Density (23 °C) *                           | ISO 1183-2    | kg/m <sup>3</sup> | 950           |
| Tensile Strength at Yield *                 | ISO 527-3     | MPa               | 26            |
| Tensile Strength at Break*                  | ISO 527-3     | MPa               | 32            |
| Tensile Strain at Break *                   | ISO 527-3     | %                 | 1000          |
| Flexural Modulus *                          | ISO 178       | MPa               | 1400          |
| IZOD Impact Strength (notched, 23 °C) *     | ISO 180/ A    | kJ/m <sup>2</sup> | 15            |
| Vicat Softening Temperature *               | ISO 306/A 120 | °C                | 127           |
| Shore D Hardness *                          | ISO 868       | -                 | 64            |
| ESCR F50 B (10% Igepal CO-630) *            | ASTM D 1693   | h                 | 180           |
| OIT (200 °C) *                              | EN 728        | min               | 7             |

Typical properties, not to be used as specification.

\* Average mechanical property values of several measurements carried out on standard pressed specimens (ISO 293) conditioned at room temperature (ISO 291).

#### PROCESSING

**TIPELIN BS 501-17** can be used in conventional extrusion machines. Recommended processing temperatures are 180-220 °C.

# TECHNICAL DATA SHEET

## POLYETHYLENE TIPELIN BS 501-17

### HDPE for blow moulding

TIPELIN / TIPOLEN / TIPPLEN / TATREN / BRALEN

The joint product portfolio of TVK and SLOVNAFT provides infinite opportunities

## STORAGE AND HANDLING

Pellets are packed in 25 kg PE-LD bags and transported on stretch-wrapped pallets at eligible load of polymer 1375 kg. Heat treated pallets are available as well. We use adhesive between the bags in order to avoid their slipping. Pay attention to this fact during the removing of the bags from the pallets. The preferred method is to lift the bag at first without rotation. Transportation in a road silo or rail silo is also available. For more detailed information please contact SLOVNAFT and TVK sales representative.

Since polyethylene is a combustible substance, the fire safety rules applicable for combustible materials in warehouses and store rooms should be observed.

If polymer is stored in conditions of high humidity and fluctuating temperatures, then atmospheric moisture can condense inside the packing. If it happened, it is recommended the pellets to be dried before use. During the storage polyethylene should not be exposed to UV radiation and temperatures above 40°C. Producer does not take responsibility for any damages caused by adverse storage.

## REACH STATEMENT

Polymers are exempt of REACH registration. However, their raw materials which mean monomers and relevant additives have been registered. TVK Plc. is committed to fully respect legislation and will only use REACH compliant raw materials. At this point in time HDPE TIPELIN does not contain any substances specifically identified as SVHC at levels greater than 0.1%.

## SAFETY

See MSDS.

## RECYCLING

Polyethylene resins are suitable for recycling using modern recycling methods. In-house production waste should be kept clean to facilitate direct recycling.

## DISCLAIMER

The information provided in this publication has been compiled to the best of our present knowledge. However, in view of the various applications of polyethylene resins and the equipment used, the processing conditions may differ.

The recommendations and data herein are to be construed as informational only and do not relieve users from carrying out their own tests and experiments prior to processing in order to check suitability for a specific use. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed. Our products are under continuous development, therefore we reserve the right to change the information presented in this brochure at our own discretion.

The REACH statement herein does not constitute legal advice. The REACH statement is provided for informational purpose only.

**TECHNICAL DATA SHEET**  
**POLYETHYLENE TIPELIN BS 501-17**  
**HDPE for blow moulding**

**TIPELIN / TIPOLEN / TIPPLEN / TATREN / BRALEN**

The joint product portfolio of TVK and SLOVNAFT provides infinite opportunities

**MANUFACTURER**

**TVK Plc.**

H-3581 Tiszaújváros,

P.O. Box: 20

Hungary

Internet: [www.tvk.hu](http://www.tvk.hu)

E-mail: [tvkinfo@tvk.hu](mailto:tvkinfo@tvk.hu)

**TECHNICAL SERVICE**

**TVK Plc.**

Polymers Marketing and Sales

Polymer Technical Service

Telephone: +36 49 522 607; +36 80 204 249

+36 49 521 540; +36 80 204 248

Fax: +36 49 886 491

E-mail: [customerservice@tvk.hu](mailto:customerservice@tvk.hu)

**SALES ORGANIZATION**

**SLOVNAFT, a.s.**

Polymer Sales

Vlčie hrdlo 1

824 12 Bratislava

Slovak Republic

Telephone: + 421 2 5859 7515

+ 421 2 5859 7741

+ 421 2 5859 7231

E-mail: [polymersales@slovnaft.sk](mailto:polymersales@slovnaft.sk)

**TVK Plc.**

H-3581 Tiszaújváros,

P.O. Box: 20

Hungary

Telephone: +36 49 521 355

Fax: +36 49 886 491

E-mail: [polymersales@tvk.hu](mailto:polymersales@tvk.hu)

**MOL Germany GmbH.**

Im Trutz Frankfurt 49

D-60322 Frankfurt am Main

Germany

Telephone: +49 69 154 04 0

Fax: +49 69 154 04 41

E-mail: [polymersales@molgermany.de](mailto:polymersales@molgermany.de)

**MOL- Austria Handels GmbH.**

Walcherstrasse 11A, 7. Stock

A-1020 Wien

Austria

Telephone: +43 1 211 20 1120

Fax: +43 1 211 20 1198

E-mail: [JHauk@molaustria.at](mailto:JHauk@molaustria.at)

**TECHNICAL DATA SHEET**  
**POLYETHYLENE TIPELIN BS 501-17**  
**HDPE for blow moulding**

**TIPELIN / TIPOLEN / TIPPLEN / TATREN / BRALEN**

The joint product portfolio of TVK and SLOVNAFT provides infinite opportunities

**TVK Italia S.r.l.**

Via Teulié, 1  
20136 Milano  
Italy  
Telephone: +39 02 58 30 5523  
Fax: +39 02 58 30 3492  
E-mail: [tvkitaly@it.tvk.eu](mailto:tvkitaly@it.tvk.eu)

**French Liaison Representative**

Paris  
France  
Mobile Phone: + 33 7 89 86 10 64  
Telephone: + 33 1 64 32 44 17  
E-mail: [husson.iren@fr.tvk.eu](mailto:husson.iren@fr.tvk.eu)

**MOL Ukraine LLC**

04655 Kiev  
Moskovskiy ave, 23, 7th floor  
Ukraine  
Telephone: +380 44 374 00 80  
+380 67 463 58 69  
Fax: +380 44 374 00 90  
E-mail: [JZavojko@mol-ukraine.com.ua](mailto:JZavojko@mol-ukraine.com.ua)

**SLOVNAFT Polska S.A.**

**PetChem Department**  
ul. Wąwozowa 23/12  
PL 02-796 Warszawa  
Poland  
Telephone: +48 22 545 70 70  
Fax: +48 22 545 70 60  
E-mail: [petchem@slovnaft.pl](mailto:petchem@slovnaft.pl)

**TIFON d.o.o.**

Savska cesta 41/XIII  
HR – 10000 Zagreb  
Croatia  
Telephone: +385 1 6160 600  
Fax: +385 1 6160 601  
E-mail: [polymersales@tifon.hr](mailto:polymersales@tifon.hr)

**SC. MOL Romania P.P. SRL**

Str. Danielopolu 4-6  
ET2 Sector 1 Cod 014 134  
Bucuresti  
Romania  
Telephone: +40 21 204 85 00  
+40 21 204 85 02  
Fax: +40 21 232 10 59  
E-mail: [petchem@molromania.ro](mailto:petchem@molromania.ro)

**Other European Countries**

Telephone: +36 49 521 355  
+36 70 458 4563  
+36 70 373 9209  
Fax: +36 49 886 491  
E-mail: [polymersales@tvk.hu](mailto:polymersales@tvk.hu)